

Product Information

VESTAKEEP® i2 P

IMPLANT GRADE VESTAKEEP® POWDER



VESTAKEEP® i2 P is a medium-viscosity polyether ether ketone (PEEK) powder that is designed for long term human implant applications.

Proven Biocompatibility of VESTAKEEP® i-Grades

VESTAKEEP® i2 P is compliant with ASTM F2026 "Standard Specification for Polyetheretherketone (PEEK) Polymers for Surgical Implant Applications".

The extra high purity and extended quality measures make the i-grades an ideal material for long term body contact.

A summary of biocompatibility tests is available upon request.

Biocompatibility tests available for VESTAKEEP® i2 P

STANDARD	DESCRIPTION
ISO 10993-12	GC/MS Fingerprint of extractable organic substances
USP CLASS VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation
ISO 10993-5	Cytotoxicity
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Maximization test according to Magnusson and Kligman
ISO 10993-11	Subchronic Systemic Toxicity
ISO 10993-3	Genotoxicity: Ames Test
ISO 10993-3	Genotoxicity: Chromosome Aberration test
ISO 10993-3	Genotoxicity: Mouse Lymphoma test
ISO 10993-6	Test for local effects after Implantation in bone (90 days)
ISO 10993-4	Haemocompatibility

In addition to the body contact period the suitability of the material depends on further criteria, for example the nature of the contact, the processing, or the surface. In any case the suitability has to be verified for the end product.

Processing of VESTAKEEP® i-Grades

As a powder, VESTAKEEP® i2 P can be used for compounding, compression molding and other melt processing.

For information about processing of VESTAKEEP® powders, please follow the general recommendations in our brochure "VESTAKEEP® Polyether Ether Ketone Powder".

Delivery of VESTAKEEP® i-Grades

VESTAKEEP® i2 P is supplied as powder in boxes with moisture-proof polyethylene liners.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector
Medical Devices

Delivery form
Powder

Conformity
Biocompatibility, Medical application

Additives
Unfilled

Mechanical properties ISO	dry	Unit	Test Standard
Tensile modulus	3600	MPa	ISO 527
Yield stress	100	MPa	ISO 527
Yield strain	5	%	ISO 527
Stress at break	80	MPa	ISO 527
Nominal strain at break, tB	30	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-
Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-

Thermal properties	dry	Unit	Test Standard
Vicat softening temperature A, 10 N, 50 K/h	335	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	310	°C	ISO 306

Physical properties	dry	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183
Density	1300	kg/m ³	ASTM D 792

Rheological properties

Melt volume-flow rate, MVR

dry
Unit
Test Standard
70

cm³/10min

ISO 1133

Temperature

380

°C

-

Load

5

kg

-

Test specimen production

Injection Molding, melt temperature

380

°C

ISO 294

Injection Molding, mold temperature

180

°C

ISO 294

Injection Molding, injection velocity

200

mm/s

ISO 294

Characteristics
Regulatory

US Pharmacopeia Class VI conformity

Chemical Resistance

General chemical resistance

Color

Natural color

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com