

Product Information

VESTAKEEP® iC 2630 G**CARBON FIBER-REINFORCED, IMPLANTABLE-GRADE POLYETHER ETHER KETONE COMPOUND FOR LONG-TERM IMPLANTS**

VESTAKEEP® iC 2630 G is a black polyether ether ketone (PEEK) resin. It contains 30% carbon fiber to increase stiffness.

Biocompatibility

VESTAKEEP® iC 2630 G is especially designed for long term implantable medical devices. The compound composition is optimized for high biocompatibility and mechanical, thermal and chemical resistance.

VESTAKEEP® iC 2630 G is a development material, biocompatibility testing is planned.

The biocompatibility testing program will follow ISO 10993-1 recommendations for permanent tissue/bone contact and USP Class VI.

Planned biocompatibility tests for VESTAKEEP® iC 2630 G

STANDARD	DESCRIPTION
ISO 10993-12	GC/MS Fingerprint of extractable organic substances
USP CLASS VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation
ISO 10993-5	Cytotoxicity
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Maximization test according to Magnusson and Kligman
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-3	Genotoxicity: Ames Test
ISO 10993-3	Genotoxicity: Mouse Lymphoma test
ISO 10993-11	Subchronic Systemic Toxicity (28 days)
ISO 10993-6	Test for local effects after Implantation in bone (28, 90, 180 days)
ISO 10993-11	Material-mediated pyrogenesis

Processing

VESTAKEEP® iC 2630 G can be processed by common melt processing techniques like injection molding and extrusion. For injection molding, we recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a temperature range from 160°C to 200°C, preferably 180°C.

Delivery

VESTAKEEP® iC 2630 G is supplied as cylindrical pellets in hobbcks containing 5 kg or 10kg. Polyethylene bags are used as primary packaging.

The results shown have been generated from a low number of production lots.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector

Medical Devices

Processing

Injection molding

Delivery form

Pellets, Granules

Optics

Opaque

Resistance to

Heat (thermal stability), Hydrolysis / hot water, Wear / abrasion, Fatigue resistance, Oil / fuels

Conformity

Biocompatibility, Medical application

Additives

Carbon fibers

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	22700	MPa	ISO 527
Stress at break	234	MPa	ISO 527
Strain at break, B	1.7	%	ISO 527

Physical properties

	dry	Unit	Test Standard
Density	1400	kg/m ³	ISO 1183
Water absorption	0.04	%	Sim. to ISO 62
Density	1400	kg/m ³	ASTM D 792

Rheological properties

	dry	Unit	Test Standard
Melt volume-flow rate, MVR	18	cm ³ /10min	ISO 1133
Temperature	400	°C	-
Load	5	kg	-

Characteristics

Applications

Medical implants

Regulatory

US Pharmacopeia Class VI conformity

Delivery form

Cylindrical pellets

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com