

Product Information

VESTAKEEP® iC 4800 R**STOCKSHAPES BASED ON POLYETHER ETHER KETONE WITH ENHANCED OSSEOINTEGRATION FOR LONG TERM IMPLANTABLE MEDICAL DEVICES**

VESTAKEEP® iC4800 R is a rod stock based on implantable grade polyether ether ketone resin VESTAKEEP® iC4800 G. It contains calcium phosphates to enhance osseointegration. It therefore belongs to the VESTAKEEP® Fusion product family.

Biocompatibility

The base resin VESTAKEEP® iC4800 G is especially designed for long term implantable medical devices. The compound composition is optimised for high biocompatibility and mechanical, thermal and chemical resistance.

The biocompatibility testing program follows ISO 10993-1 recommendations for permanent tissue/bone contact and USP Class VI.

Available biocompatibility reports for VESTAKEEP® iC4800 G

STANDARD	DESCRIPTION
ISO 10993-12	GC/MS Fingerprint of extractable organic substances
USP CLASS VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation
ISO 10993-5	Cytotoxicity
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Maximization test according to Magnusson and Kligman
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-3	Genotoxicity: Ames Test
ISO 10993-3	Genotoxicity: Mouse Lymphoma test
ISO 10993-11	Subchronic Systemic Toxicity (28 days)
ISO 10993-6	Test for local effects after Implantation in bone (28, 90, 180 days)
ISO 10993-11	Material-mediated pyrogenes

Delivery

VESTAKEEP® iC4800 R is supplied as stock shapes with a diameter of 10 mm and 20 mm with a length of 3000 mm. Further it is supplied with 40 mm diameter with a length of 2000 mm. Other diameters and lengths are possible.

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector

Medical Devices

Processing

Machining

Delivery form

Stock shape (rods and plates)

Resistance to

Heat (thermal stability), UV / light / weathering

Electrical

Insulating

Conformity

Biocompatibility, Medical application

Additives

Mineral fillers

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	4700	MPa	ISO 527
Yield stress	105	MPa	ISO 527
Yield strain	4	%	ISO 527
Nominal strain at break, tB	10	%	ISO 527
Izod Impact notched, 23°C	4.5	kJ/m ²	ISO 180/1A
Type of failure	C	-	-
Flexural modulus, 23°C	4700	MPa	ISO 178
Flexural strength, 23°C	165	MPa	ISO 178

Thermal properties

	dry	Unit	Test Standard
Melting temperature	340	°C	ISO 11357-1/-3
Glass transition temperature, 2 nd heating, onset	145	°C	ISO 11357
Glass transition temperature, 2 nd heating, midpoint	155	°C	ISO 11357
Recrystallization temperature, 10 K/min	285^[e]	°C	ISO 11357
Melting Temperature	340	°C	ASTM D 3418

e: 20 K/minute

Physical properties

	dry	Unit	Test Standard
Density	1460	kg/m ³	ISO 1183
Density	1460	kg/m ³	ASTM D 792

Characteristics

Applications

Medical implants

Special Characteristics

PTFE-free, High impact strength, Semi-crystalline, High viscosity, Self-extinguishing

Features

Low odor, Non-corrosive

Color

Grey

Additives

Inorganic fillers

Chemical Resistance

Acid resistance, Solvent resistance, Oxidation resistance, Radiation resistance, General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com