

LNPT[™] LUBRICOMP[™] COMPOUND LCL36E

LCL-4036 EM
REGION EUROPE

DESCRIPTION

LNP LUBRICOMP LCL36E compound is based on Polyetheretherketone (PEEK) resin containing 30% carbon fiber and 15% PTFE. Added features of this grade include: Easy Molding, Wear Resistant, Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength, High temperature resistance
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	224	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	21600	MPa	ISO 527
Flexural Stress, break, 2 mm/min	317	MPa	ISO 178
Flexural Modulus, 2 mm/min	19800	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	8.4E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.2E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	>300	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.5	g/cm ³	ISO 1183
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.E+01 – 1.E+03	Ω	ASTM D257
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120 – 150	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	380 – 390	°C	
Front - Zone 3 Temperature	380 – 395	°C	
Middle - Zone 2 Temperature	365 – 375	°C	
Rear - Zone 1 Temperature	350 – 360	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.