

Technical Data Sheet

Hostacom PPT X9127 T 3143 DK SHADOW



Polypropylene Compounds

Product Description

Hostacom PPT X9127 T 3143 is an unfilled polypropylene copolymer, with high impact resistance and good UV resistance.

Product is available as a customized color matched, pellet form. This grade is delivered in 3143 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application Interior Trims

Market Automotive

Processing Method Injection Meld

Processing Method Injection Molding

Attribute High Flow; High Impact Resistance; UV Resistant

	Nominal		Test Method
Typical Properties	Value	Units	
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	1250	MPa	ISO 178
Tensile Stress at Yield	22	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	37	kJ/m²	ISO 180/1A