

## **Technical Data Sheet**

## Hostacom PPU X9057HS C11354



Polypropylene Compounds

## **Product Description**

*Hostacom* PPU X9057HS is an unfilled PP copolymer, with medium flowability, high rigidity and good impact resistance.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

**Application** Automotive Parts; Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Good Abrasion Resistance; Good Color Stability; Good Flow; Good Impact

Resistance; Good Stiffness; Good Surface Finish; Low Density; Low to No Odor; Low

VOC Emission; Scratch Resistant; UV Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	11	g/10 min	ISO 1133-1
Density, (23 °C)	0.91	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1400	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched			
(23 °C)	8	kJ/m²	ISO 179-1/1eA
(0 °C)	5	kJ/m²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2