

## Technical Data Sheet

### Hostacom PPU X9067HS 305514



Polypropylene Compounds

#### Product Description

Hostacom PPU X9067HS 305514 is an unfilled PP copolymer, with high melt flow rate, high toughness and increased stiffness. This grade is delivered in 305514 color version. This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Crystalline; High Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	13	g/10 min	ISO 1133-1
Density, (23 °C)	0.91	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1450	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	26	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	10	kJ/m <sup>2</sup>	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179-1/1eU