

## Technical Data Sheet

### Hostacom TKC 2007N NA ZA2 SHETLA



Polypropylene Compounds

#### Product Description

Hostacom TKC 2007N NA ZA2 SHETLA is a 5% talc filled impact modified resin that is typically used for interior applications. It has excellent impact-stiffness balance, good flowability and very good scratch performance.

<b>Application</b>	Automotive Parts; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Impact Resistance; Good Moldability; Good Stiffness; Impact Modified; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	14	g/10 min	ASTM D1238
Density	0.93	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1550	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	25	kJ/m <sup>2</sup>	ISO 179
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			