

Technical Data Sheet

Hostacom TKC 420N NA 82V TITAN SCH



Polypropylene Compounds

Product Description

Hostacom TKC 420N NA 82V TITAN SCH is a 12% Talc filled, impact modified grade that is typically used for interior applications that has excellent impact/stiffness balance, good flowability properties and very good scratch resistance. It has an outstanding blooming resistance at elevated temperatures.

Application Automotive Parts; Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Good Flow; Good Impact Resistance; Good Stiffness; Scratch Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C, 2 mm/min)	1600	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	35	kJ/m²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.6	kJ/m²	ISO 179
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.