lyondellbasell

Hostacom TKC717D

Compounded Polyolefin

Product Description

This information has been secured during the course of product development. Both the product and its properties are subject to change before final commercialization.

Hostacom TKC717D medium melt flow, 2,200 MPa flexural modulus, precolored, UV-stabilized, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of stiffness, impact resistance and processability. It was designed primarily for automotive interior applications that require high durability.

Product Characteristics				
Test Method used ISO				
Processing Methods Injection Moldin		ıg		
Features	Good Dimensional Stability, High Impact Resistance , Good Moldability , High Rigidity , Scratch Resistant, Good Weather Resistance			
Typical Customer Applications	Instrument Panels			
Typical Properties		Method	Value	Unit
Physical				
Density		ISO 1183	1.05	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)		ISO 1133	12	g/10 min
Note: Alternative test method is AST	M D 1238-01.			
Mechanical				
Tensile Stress at Yield		ISO 527-1, -2	22	MPa
Tensile Strain at Yield		ISO 527-1, -2	6	%
Flexural modulus		ISO 178	2200	MPa
Impact				
Notched izod impact strength (23 °C)		ISO 180	43	kJ/m²
Thermal				
Heat deflection temperature B (0.45 MPa) Unannealed		ISO 75B-1, -2	105	°C
Heat deflection temperature A (1.80 MPa) Unannealed		ISO 75A-1, -2	59	°C
CLTE, Flow		ISO 11359-1, - 2	4.1 x 10-5	cm/cm/°C
<i>Note</i> : Determined over a temperatur ASTM E 228-95.	e range of -30°C	to 100°C. Alterr	native test m	ethod is
Additional Information				
Mold shrinkage		ISO 294-4		