lyondellbasell

Hostacom TKC717N

Compounded Polyolefin

Product Description

Hostacom TKC717N medium melt flow, 2,200 MPa flexural modulus, precolored, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent combination of stiffness, impact resistance and processability. It was designed primarily for automotive interior applications that require high durability.

UV-stabilized, precolored versions are also available as *Hostacom* TKC717D.

| Product Characteristics | | | | |
|---|--|---------------|-------|----------|
| Test Method used | used ISO | | | |
| rocessing Methods Injection Moldir | | ıg | | |
| Features | Medium Flow, High Impact Resistance,Good Moldability, High Rigidity,Scratch Resistant | | | |
| Typical Customer Applications | Instrument Panels | | | |
| Typical Properties | | Method | Value | Unit |
| Physical | | | | |
| Density | | ISO 1183 | 1.05 | g/cm³ |
| Melt flow rate (MFR) (230°C/2.16Kg) | | ISO 1133 | 12 | g/10 min |
| Note: Alternative test method is AS | TM D 1238-01. | | | |
| Mechanical | | | | |
| Tensile Stress at Yield | | ISO 527-1, -2 | 22 | MPa |
| Tensile Strain at Yield | | ISO 527-1, -2 | 6 | % |
| Flexural modulus | | ISO 178 | 2200 | MPa |
| Impact | | | | |
| Notched izod impact strength (23 °C) | | ISO 180 | 43 | kJ/m² |
| Thermal | | | | |
| Heat deflection temperature B (0.45 | MPa) Unannealed | ISO 75B-1, -2 | 105 | °C |
| Heat deflection temperature A (1.80 MPa) Unannealed | | ISO 75A-1, -2 | 59 | °C |
| Additional Information | | | | |
| Mold shrinkage | | ISO 294-4 | | |
| | | | | |