

Technical Data Sheet

Hostacom TRC 2367N C11675



Polypropylene Compounds

Product Description

Hostacom TRC 2367N C11675 is a talc filled PP copolymer, with good flowability, excellent impact/stiffness balance and high scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11675 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| | |
|-------------------|------------------------|
| Application | Instrument Panels |
| Market | Automotive |
| Processing Method | Injection Molding |
| Attribute | Good Impact Resistance |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 20 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 1.04 | g/cm ³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 2000 | MPa | ISO 178/A1 |
| Impact | | | |
| Notched Izod Impact Strength | | | |
| (23 °C) | 40 | kJ/m ² | ISO 180/1A |
| (-30 °C) | 3.5 | kJ/m ² | ISO 180/1A |
| Thermal | | | |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 106 | °C | ISO 75B-1, -2 |