

Technical Data Sheet

Hostacom TRC 352N C6 C15207



Polypropylene Compounds

Product Description

"Hostacom" TRC352N C6 is a 20% mineral filled, impact modified grade for interior applications with excellent stiffness/impact balance, very good flowability properties and excellent scratch resistance. It has an outstanding blooming resistance at elevated temperatures. The grade is available in color-matched, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Moldability; High Rigidity; Medium Flow; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1900	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	40	kJ/m²	ISO 179-1/1eA
(-30 °C)	4	kJ/m²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2