

## Technical Data Sheet

### Hostacom TRC 411N D71500



Polypropylene Compounds

#### Product Description

Hostacom TRC 411N is a 15% talc filled PP copolymer compound with high flowability, good impact/stiffness balance and excellent scratch resistance, offering low odour and low emissions performances.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Automotive Parts; Instrument Panels; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Ductile; Good Abrasion Resistance; Good Color Stability; Good Processability; Good Stiffness; Good Surface Finish; High Flow; High Impact Resistance; Low Density; Low Temperature Impact Resistance; Low to No Odor; Low VOC Emission; Pleasing Surface Appearance; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	19	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C)	30	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2