

## **Technical Data Sheet**

## Hostacom X M2 V05 C11354

LYB LyondellBasell

Polypropylene Compounds

## **Product Description**

*Hostacom* X M2 V05 is a 20% talc filled PP copolymer, with good flowability, high stiffness, good impact resistance and very good processability.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application Automotive Parts; Instrument Panels; Interior Automotive Applications; Interior Trims

Market Automotive

Processing Method Injection Molding

Attribute Good Abrasion Resistance; Good Color Stability; Good Flow; Good Impact

Resistance; Good Processability; Good Surface Finish; High Stiffness; Low to No

Odor

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	4	kJ/m²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2