

Technical Data Sheet

**Petrothene NA480178**



Ethylene Vinyl Acetate

**Product Description**

*Petrothene* NA480178 is a LDPE/EVA copolymer resin selected by customers for specialty films. NA480178 produces film with excellent puncture resistance, impact strength, heat sealability, clarity and low temperature flexibility. Typical applications include frozen food packaging, bundling, heavy-duty, and stretch hooder films.

<b>Application</b>	Agriculture Film; Bags & Pouches; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Liner Film; Sealants; Shrink Film; Stretch Hood
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Blown Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.25	g/10 min	0.25	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.923	g/cm <sup>3</sup>	0.923	g/cm <sup>3</sup>	ASTM D1505
Product Density, (23 °C)	0.930	g/cm <sup>3</sup>	0.930	g/cm <sup>3</sup>	ASTM D1505
Vinyl Acetate Content	4.5	%	4.5	%	LYB Method
<b>Film</b>					
Dart Drop Impact Strength, F50	320	g	320	g	ASTM D1709
Tensile Strength at Break					
MD	3200	psi	22.1	MPa	ASTM D882
TD	3000	psi	20.7	MPa	ASTM D882
Tensile Elongation at Break					
MD	370	%	370	%	ASTM D882
TD	550	%	550	%	ASTM D882
1% Secant Modulus					
MD	19000	psi	131	MPa	ASTM D882
TD	23000	psi	159	MPa	ASTM D882
Elmendorf Tear Strength					
MD	150	g	150	g	ASTM D1922
TD	250	g	250	g	ASTM D1922
<b>Thermal</b>					
Vicat Softening Temperature	190	°F	88	°C	ASTM D1525
<b>Additive</b>					
Slip	None		None		LYB Method
Antiblock	12000	ppm	12000	ppm	LYB Method