

## Technical Data Sheet

### *Alathon* L4903



High Molecular Weight High Density Polyethylene

#### Product Description

*Alathon* L4903 is a high molecular weight high density copolymer with broad bimodal molecular weight distribution. This resin exhibits excellent machine direction tear in an HMW-HD resin as well as low gel levels. Typical applications include trash can liners and products requiring incorporation of PCR.

<b>Application</b>	Bags & Pouches; Can Liners; Retail Carryout Bags; Specialty Film
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Blown Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.027	g/10 min	0.027	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm <sup>3</sup>	0.949	g/cm <sup>3</sup>	ASTM D1505
<b>Film</b>					
Dart Drop Impact Strength, F50	230	g	230	g	ASTM D1709
Tensile Strength at Break					
MD	11600	psi	80.0	MPa	ASTM D882
TD	7600	psi	52.4	MPa	ASTM D882
Tensile Strength at Yield					
MD	5400	psi	37.2	MPa	ASTM D882
TD	4100	psi	28.3	MPa	ASTM D882
Tensile Elongation at Break					
MD	330	%	330	%	ASTM D882
TD	410	%	410	%	ASTM D882
Secant Modulus					
MD	144000	psi	993	MPa	ASTM D882
TD	148000	psi	1020	MPa	ASTM D882
Elmendorf Tear Strength					
MD	10	g	10	g	ASTM D1922
TD	60	g	60	g	ASTM D1922

## Notes

Film data obtained from sample produced on an Alpine 200 mm line equipped with a three layer die (40/35/25), three extruders (65 mm/75 mm/50 mm), internal bubble cooling, die gap of 1.5 mm, neck height of 8 x DD, blow up ratio of 4:1, film thickness of 0.8 mil and operating at 500 lbs/hr.

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.