

Technical Data Sheet

lcorene N2805-500 NAT0000XX



High Density Polyethylene

Product Description

lcorene N2805 is a premium HDPE powder with a good balance between the processability and mechanical properties. This grade has high gloss and high dimensional stability and is suitable for use in masterbatch or carpetbacking applications.

Attribute	Food Contact Acceptable; Good Dimensional Stability; Good Processability; High Gloss
Forms	Powder
Application	Automotive Interior Trim; Carpet Backing; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density	0.954	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	23	MPa	ASTM D638
Flexural Modulus	850	MPa	ASTM D790
Tensile Elongation at Break	>100	%	ASTM D638
Hardness			
Durometer Hardness, (Shore D)	65		ASTM D2240
Thermal			
Vicat Softening Temperature	127	°C	ASTM D1525
Peak Melting Temperature	133	°C	ASTM D3418

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.