

## Technical Data Sheet

### *Petrothene* LT493501

High Density Polyethylene

#### Product Description

*Petrothene* LT493501 is a high density copolymer natural resin used by customers for conduit with demanding environmental stress crack resistance requirements. LT493501 offers an excellent balance of stiffness, toughness and ease of processing.

Conduit made with this resin is used with fiber optic cable, electrical cable and telecommunications cable. LT493501 meets the material requirements for polyethylene conduit as per ASTM F2160 and also meets the requirements of ASTM D3350 cell classification 435530A.

<b>Application</b>	Conduit
<b>Market</b>	Industrial, Building & Construction; Pipe
<b>Processing Method</b>	Pipe; Sheet and Profile Extrusion
<b>Attribute</b>	Excellent Processability; High ESCR (Environmental Stress Cracking Resistance)

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.34	g/10 min	0.34	g/10 min	ASTM D1238
Density, (23 °C)	0.948	g/cm <sup>3</sup>	0.948	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>					
Flexural Modulus, (2% Secant)	131600	psi	900	MPa	ASTM D790
Tensile Strength at Yield	3500	psi	24.1	MPa	ASTM D638
Tensile Elongation at Break	>600	%	>600	%	ASTM D638
Environmental Stress Crack Resistance					
F <sub>10</sub> (10% Igepal®, Cond B)	>96	hr	>96	hr	ASTM D1693
F <sub>50</sub> (100% Igepal®, Cond B)	>1000	hr	>1000	hr	ASTM D1693
<b>Thermal</b>					
Low Temperature Brittleness	<-101	°F	<-74	°C	ASTM D746
DSC Induction Temperature	>473	°F	>245	°C	ASTM D3350

## Notes

Igepal® is a registered trademark of Rhodia.

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.