

## **Technical Data Sheet**

# Petrothene LT602902

High Density Polyethylene



# **Product Description**

*Petrothene* LT602902 is a high density polyethylene sheet extrusion grade with excellent extrusion characteristics and low warpage. The resulting sheet exhibits good stiffness and impact properties. Typical applications include sheet for signage and packaging.

**Application** General Sheet Extrusion; Housewares; Structural Parts

Market Rigid Packaging

Processing Method Extrusion Blow Molding; Sheet and Profile Extrusion

Attribute Good Processability

| Typical Properties                                      | Nominal<br>Value | English<br>Units | Nominal<br>Value | SI<br>Units | Test Method |
|---|------------------|------------------|------------------|-------------|-------------|
| Physical  |                  |                  |                  |             |             |
| Melt Flow Rate, (190 °C/2.16 kg)                        | 0.30             | g/10 min         | 0.30             | g/10 min    | ASTM D1238  |
| Density, (23 °C)  | 0.960            | g/cm³            | 0.960            | g/cm³       | ASTM D1505  |
| Mechanical  |                  |                  |                  |             |             |
| Flexural Modulus, (1% Secant)                           | 225300           | psi              | 1550             | MPa         | ASTM D790   |
| Tensile Strength at Yield                               | 4390             | psi              | 30.3             | MPa         | ASTM D638   |
| Tensile Elongation at Break                             | 1400             | %                | 1400             | %           | ASTM D638   |
| Impact  |                  |                  |                  |             |             |
| Tensile Impact Strength                                 | 101              | ft-lb/in²        | 212              | kJ/m²       | ASTM D1822  |
| Thermal   |                  |                  |                  |             |             |
| Vicat Softening Point                                   | 261              | °F               | 127              | °C          | ASTM D1525  |
| Low Temperature Brittleness, F <sub>50</sub>            | <-105            | °F               | <-76             | °C          | ASTM D746   |
| Deflection Temperature Under Load, (66 psi, Unannealed) | 167              | °F               | 75               | °C          | ASTM D648   |

### **Notes**

These are typical property values not to be construed as specification limits.

## **Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## **Company Information**

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

#### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

#### **Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 12/6/2024 Petrothene LT602902 Recipient Tracking #: Request #: 5421880