

## Technical Data Sheet

### *Petrothene* NA345184

Low Density Polyethylene

#### Product Description

*Petrothene* NA345 is a series of homopolymer resins that combine premium clarity with strength and stiffness. In addition, NA345 exhibits good impact strength on both flat and creased film. NA345 is selected by customers for textile packaging, light produce, bread bags and other thin packaging films enhanced by clarity and sparkle.

Application	Clarity Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	1.8	g/10 min	1.8	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.921	g/cm <sup>3</sup>	0.921	g/cm <sup>3</sup>	ASTM D1505
<b>Film</b>					
Dart Drop Impact Strength, F50	90	g	90	g	ASTM D1709
Tensile Strength at Break					
MD	4000	psi	27.6	MPa	ASTM D882
TD	3400	psi	23.4	MPa	ASTM D882
Tensile Strength at Yield					
MD	1500	psi	10.3	MPa	ASTM D882
TD	1600	psi	11.0	MPa	ASTM D882
Tensile Elongation at Break					
MD	300	%	300	%	ASTM D882
TD	500	%	500	%	ASTM D882
1% Secant Modulus					
MD	26000	psi	179	MPa	ASTM D882
TD	30000	psi	207	MPa	ASTM D882
Elmendorf Tear Strength					
MD	360	g	360	g	ASTM D1922
TD	200	g	200	g	ASTM D1922
<b>Thermal</b>					
Vicat Softening Temperature	212	°F	100	°C	ASTM D1525
<b>Optical</b>					
Haze	5.0	%	5.0	%	ASTM D1003
As measured on NA345196 (medium slip, medium antiblock).					
Gloss, (45°)	70		70		ASTM D2457
As measured on NA345196 (medium slip, medium antiblock).					
<b>Additive</b>					
Slip	None		None		LYB Method
Antiblock	1500	ppm	1500	ppm	LYB Method