

## **Technical Data Sheet**

## *Icorene* 3560 GRY 7767

Linear Low Density Polyethylene



## **Product Description**

*Icorene* 3560 is a linear low density polyethylene specifically developed for rotational moulding. This grade is suitable for use in general purpose applications. It has a good balance of properties such as toughness, easy flow and stiffness.

Processing Method Rotomolding

Attribute Good Flow; Good Processability; Good Stiffness; Good Toughness; UV Resistant

Forms Powder

Appearance Natural Color; Unspecified Color

Additive UV Stabilizer

**Application** Containers; General Purpose; Tanks

|   | Nominal |          |             |
|---|---------|----------|-------------|
| Typical Properties  | Value   | Units    | Test Method |
| Physical  |         |          |             |
| Melt Flow Rate, (190 °C/2.16 kg)  | 5.0     | g/10 min | ASTM D1238  |
| Density   | 0.935   | g/cm³    | ASTM D1505  |
| Mechanical  |         |          |             |
| Tensile Strength at Yield   | 17      | MPa      | ASTM D638   |
| Environmental Stress Crack Resistance, (Condition B, F50, 100% Igepal, 50 °C) | >150    | hr       | ASTM D1693  |
| Flexural Modulus  | 550     | MPa      | ISO 178     |
| Impact  |         |          |             |
| Drop Impact Resistance, (-20 °C, Internal Method)                             | 170     | J/cm     | ASTM D4226  |
| Hardness  |         |          |             |
| Durometer Hardness, (Shore D)   | 55      |          | ASTM D2240  |
| Thermal   |         |          |             |
| Deflection Temperature Under Load Unannealed (264 psi)                        | 36      | °C       | ASTM D648   |
| Deflection Temperature Under Load Unannealed (66 psi)                         | 52      | °C       | ASTM D648   |
| Peak Melting Temperature  | 125     | °C       | ASTM D3418  |