

## **Technical Data Sheet**

## Icorene 3590 GRY 7750

Linear Low Density Polyethylene



## **Product Description**

*Icorene* 3590 is a linear low density polyethylene specifically developed for rotational moulding. This grade is a very fast processing material suitable for use in many different applications. It has a good balance of properties such as toughness, easy flow and stiffness.

Processing Method Rotomolding

Attribute Good Flow; Good Moldability; Good Processability; Good Stiffness; Good Toughness;

**UV** Resistant

Forms Powder

Appearance Natural Color; Unspecified Color

Additive UV Stabilizer

**Application** General Purpose

|   | Nominal |          |             |
|---|---------|----------|-------------|
| Typical Properties  | Value   | Units    | Test Method |
| Physical  |         |          |             |
| Melt Flow Rate, (190 °C/2.16 kg)  | 9.0     | g/10 min | ASTM D1238  |
| Density   | 0.935   | g/cm³    | ASTM D1505  |
| Mechanical  |         |          |             |
| Tensile Strength at Yield   | 17.0    | MPa      | ISO 527     |
| Tensile Strength at Break   | 16.0    | MPa      | ISO 527     |
| Environmental Stress Crack Resistance, (Condition B, F50, 100% Igepal, 50 °C) | >150    | hr       | ASTM D1693  |
| Flexural Modulus  | 550     | MPa      | ISO 178     |
| Impact  |         |          |             |
| Drop Impact Resistance, (-20 °C, Internal Method)                             | 160     | J/cm     | ASTM D4226  |
| Hardness  |         |          |             |
| Durometer Hardness, (Shore D)   | 53      |          | ISO 868     |
| Thermal   |         |          |             |
| Vicat Softening Temperature, (A (10N))  | 113     | °C       | ISO 306     |
| Melting Temperature   | 126     | °C       | DSC         |
|   |         |          |             |