

(+) 18816996168

Poncioplastics.com

Technical Data Sheet

Polyflam 36N5006NG6130GRY



Polybutylene Terephthalate Alloy

Product Description

Polyflam 36N5006NG6130GRY is a Polybutylene Terephthalate Alloy material.

Forms

Pellets

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.2	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	48.3	MPa	ASTM D638
Flexural Modulus	1970	MPa	ASTM D790
Impact			
Gardner Impact	>36.2	J	ASTM D5420
Notched Izod Impact	800	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	79.4	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	107	°C	ASTM D648
RTI Elec	75	°C	UL 746B
RTI Imp	75	°C	UL 746B
RTI Str	75	°C	UL 746B
UL Information			
Flame Rating, (1.5 mm)	HB		UL 94