

Technical Data Sheet

Dexflex 1066LS-UV 2065 (EBONY)

Polypropylene Compounds

Product Description

Dexflex 1066LS-UV 2065 is a thermoplastic olefinic elastomer (TPO) used for automotive exterior applications that require excellent low-temperature toughness in large injection molded parts.

Product is available as a customized color matched, pellet form. This grade is delivered in 2065 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Low Temperature Toughness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.91	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	600	MPa	ISO 178
Tensile Stress at Yield	13	MPa	ISO 527-1, -2
Tensile Strain at Break	>300	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	50	kJ/m ²	ISO 180/1A