



Dexflex 810

Compounded Polyolefin

Product Description

 ${\it Dexflex}~810~{\rm is~a~thermoplastic~olefinic~elastomer~(TPO)~that~offers~excellent~paintability~and~processability.}$

Product Characteristics

Test Method used ISO

Processing Methods Injection Molding

Features Paintable, Good Processability

Typical Customer Applications Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.92	g/cm³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	11	g/10 min
Mechanical			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	16.5	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	850	MPa
Note: 80x10x4mm specimen			
Impact			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	16	J
Additional Information			
Mold shrinkage	ISO 294-4		