



## Dexflex 815

### Compounded Polyolefin

#### Product Description

Dexflex 815 is a thermoplastic olefinic elastomer (TPO) designed for exterior automotive applications that require a combination of stiffness, low-temperature impact resistance and excellent processability.

#### Product Characteristics

Test Method used	ISO
Processing Methods	Injection Molding
Features	Low Temperature Impact Resistance, Paintable, Good Processability, Good Stiffness
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.92	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	20	g/10 min
<b>Mechanical</b>			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	20.0	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	1050	MPa
Note: 80x10x4mm specimen			
<b>Impact</b>			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	17	J
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		