

## **Dexflex 910** Advanced Polyolefin

<b>Product Description</b> <i>Dexflex</i> 910 high melt flow, medium a good balance of properties.	n modulus, mine	ral-filled thermopla	stic elastor	neric olefin ha
Product Characteristics				
Test Method used	ASTM			
Processing Methods	Injection Molding			
Features	High Flow , High Impact Resistance			
Typical Customer Applications	Bumpers			
Typical Properties		Method	Value	Unit
Physical				
Density -Specific Gravity		ASTM D 792	0.94	
Melt Flow Rate		ASTM D 1238	25	g/10 min
Mechanical				
Flexural Modulus		ASTM D 790	1200	MPa
Tensile Strength @ Yield		ASTM D 638	17.9	MPa
Impact				
Notched Izod Impact		ASTM D 256		
(23 °C)			No Break	
(-30 °C)			85	J/m
Additional Information				
Mold shrinkage		ISO 294-4		
Note: Please contact LyondellBas	ell for shrinkage	e recommendations		
Additional Properties				
Note: All testing performed accord	ling to Honda H	ES 2503 test meth	ods.	