

## Technical Data Sheet

### Hifax BC 72 G C13055



Polypropylene Compounds

#### Product Description

Hifax BC 72G C13055 is a 10% talc filled PP copolymer, with high stiffness and good UV resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in C13055 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Color Stability; Good Surface Finish; High Flow; Low Density; Medium Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	24	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	120	°C	ISO 75B-1, -2