## **Technical Data Sheet**

## Hifax TRC 1230P 848 Black

Polypropylene Compounds

## **Product Description**

Hifax TRC 1230P 848 Black thermoplastic polyolefin is typically used for automotive and heavy-truck applications that require energy management combined with ductility, stiffness and impact resistance over a broad temperature range. This material exhibits excellent processability and dimensional stability.

(+) **18816996168** Ponciplastics.com

Application	Automotive Parts; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	1.10	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	2000	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	50	kJ/m²	ISO 179
Multi-axial Impact Strength	22	J	ASTM D3763
-20 °C			
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.

