

## Technical Data Sheet

### Hifax TYC 1168X GREY

Polypropylene Compounds

#### Product Description

Hifax TYC 1168X GREY very high melt flow for easy and fast molding and has low density, which reduces part weight and improves paint adhesion. Good stiffness and excellent cold temperature impact. It is typically used for fully painted exterior trim and fascia applications.

<b>Application</b>	Automotive Parts; Bumpers; Exterior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Dimensional Stability; Good Flow; Good Impact Resistance; Good Moldability; High Stiffness; Low Shrinkage; Low Temperature Impact Resistance; Paintable

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	35	g/10 min	ASTM D1238
Density, (23 °C, Method A)	0.98	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus, (23 °C)	1600	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	54	kJ/m <sup>2</sup>	ISO 179
(-30 °C)	5.1	kJ/m <sup>2</sup>	ISO 179
Multi-axial Impact Strength, (-30 °C, 2.2 m/s, 3.2 mm plaque)	22	J	ASTM D3763
Failure Mode Ductile.			
<b>Thermal</b>			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	52	°C	ISO 75A-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			