lyondellbasell

Hifax TYC 762PLS

Compounded Polyolefin

Product Description

This information has been secured during the course of product development. Both the product and its properties are subject to change before final commercialization.

Hifax TYC 762PLS very high melt flow, 2,100 MPa flexural modulus, precolored, UV-stabilized, mineral-filled, paintable thermoplastic elastomeric olefin has an excellent balance of properties, processability, and paintability. It was designed primarily for automotive bumper fascias.

Product Characteristics				
Test Method used	ISO			
Processing Methods	Injection Molding			
Features	Good Dimensional Stability, Good Impact Resistance , Good Moldability , Paintable, High Stiffness			
Typical Customer Applications	Exterior Applications			
Typical Properties		Method	Value	Unit
Physical				
Density		ISO 1183	1.08	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)		ISO 1133	19	g/10 min
Note: Alternative test method is AST	M D 1238-01.			
Mechanical				
Tensile Stress at Yield		ISO 527-1, -2	19	MPa
Flexural modulus		ISO 178	2100	MPa
Impact				
Notched izod impact strength		ISO 180		
(23 °C)			43	kJ/m²
(-40 °C)			4.0	kJ/m²
Hardness				
Durometer Hardness (Shore D)		ASTM D 2240	60	
Note: 15 second dwell				
Thermal				
Heat deflection temperature A (1.80 M	MPa) Unannealed	ISO 75A-1, -2	56	°C
Additional Information				
Mold shrinkage		ISO 294-4		