

Technical Data Sheet

Hostacom 0207 8049 (U024)



Polypropylene Compounds

Product Description

Hostacom 0207 8049 (U024) is an unfilled polypropylene copolymer, with very high melt flow rate offering a good impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in 8049 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; High Flow; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	41	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1450	MPa	ISO 178
Tensile Stress at Yield	24.5	MPa	ISO 527-1, -2
Tensile Strain at Break	30	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	8.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	99	°C	ISO 75B-1, -2