

## Technical Data Sheet

### Hostacom DYS 707N E G82764



Polypropylene Compounds

#### Product Description

Hostacom DYS 707N E G82764 is an unfilled PP copolymer, with high impact resistance, excellent impact/stiffness balance and very good processability. Product is available as a customized color matched, pellet form. This grade is delivered in G82764 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; High Flow

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	22	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	18	MPa	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	45	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-40 °C)	4	kJ/m <sup>2</sup>	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	40	kJ/m <sup>2</sup>	ISO 180/1A
(-40 °C)	5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2