

Technical Data Sheet

Hostacom EP3307 T 2067

Polypropylene Compounds



Product Description

Hostacom EP3307 T 2067 is an unfilled polypropylene copolymer, with high impact resistance and good UV resistance.

Product is available as a customized color matched, pellet form. This grade is delivered in 2067 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

ApplicationInterior TrimsMarketAutomotiveProcessing MethodInjection Molding

Attribute Good Flow; High Impact Resistance; UV Resistant

	Nominal		Test Method
Typical Properties	Value	Units	
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	1100	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Tensile Strain at Break	350	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	45	kJ/m²	ISO 180/1A
(-30 °C)	6	kJ/m²	ISO 180/1A