

Technical Data Sheet

Hostacom ERC 161N C11323



Polypropylene Compounds

Product Description

Hostacom ERC 161N is a 15% talc filled PP copolymer, with very good flowability, good dimensional stability, excellent impact/stiffness balance and good scratch resistance. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application Automotive Parts; Instrument Panels

Market Automotive

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2200	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	5	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2