

Technical Data Sheet

Hostacom ERC 450N T C16006



Polypropylene Compounds

Product Description

Hostacom ERC 450N T C16006 is a 10% talc filled PP copolymer, with superior flowability, good stiffness, and excellent scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C16006 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Processability; Good Stiffness; High Flow; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	29	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.98	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	2050	MPa	ISO 178
Tensile Stress at Yield	24.5	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	6.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	106	°C	ISO 75B-1, -2