## **Technical Data Sheet**

## Hostacom ERC 487N C12827

7

(+) **18816996168** Ponciplastics.com



Polypropylene Compounds

## **Product Description**

*Hostacom* ERC 487N C12827 is a 5% talc filled PP copolymer, with excellent flowability, high stiffness, high dimensional stability and excellent scratch resistance. . It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in C12827 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| Application       | Interior Trims              |
|-------------------|-----------------------------|
| Market            | Automotive                  |
| Processing Method | Injection Molding           |
| Attribute         | Good Stiffness; Low Density |

|   | Nominal |          |               |
|---|---------|----------|---------------|
| Typical Properties  | Value   | Units    | Test Method   |
| Physical  |         |          |               |
| Melt Flow Rate, (230 °C/2.16 kg)                          | 20      | g/10 min | ISO 1133-1    |
| Density, (23 °C)  | 0.95    | g/cm³    | ISO 1183-1/A  |
| Mechanical  |         |          |               |
| Flexural Modulus, (23 °C, Tech. A)                        | 1800    | MPa      | ISO 178/A1    |
| Tensile Stress at Yield, (23 °C)                          | 25      | MPa      | ISO 527-1, -2 |
| Impact  |         |          |               |
| Notched Izod Impact Strength                              |         |          |               |
| (23 °C)   | 5       | kJ/m²    | ISO 180/1A    |
| (-40 °C)  | 2       | kJ/m²    | ISO 180/1A    |
| Thermal   |         |          |               |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 101     | °C       | ISO 75B-1, -2 |