

Technical Data Sheet

Moplen HP422H

Polypropylene, Homopolymer



Product Description

Moplen HP422H is a modified polypropylene homopolymer designed for the production of BOPP films at very high speed. BOPP films produced with HP422H feature good mechanical properties, excellent barrier against moisture, odours, oxygen, good transparency and gloss. Coextruded films made of Moplen HP422H are widely used in the food packaging industry. Moplen HP422H does not contain any slip or antistatic agents and no Calcium Stearate is intentionally added.

Application Barrier Film; Food Packaging Film

Market Flexible Packaging

Processing Method BOPP

Attribute High Clarity; High Gloss; Homopolymer; Low to No Odor; Moisture Barrier

| | Nominal | | |
|---|---------|----------|---------------|
| Typical Properties | Value | Units | Test Method |
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 2.0 | g/10 min | ISO 1133-1 |
| Density | 0.900 | g/cm³ | ISO 1183-1 |
| Mechanical | | | |
| Flexural Modulus | 1450 | N/mm² | ISO 178 |
| Tensile Stress at Yield, (23 °C, 50 mm/min) | 34 | N/mm² | ISO 527-1, -2 |
| Tensile Strain at Break, (23 °C, 50 mm/min) | 410 | % | ISO 527-1, -2 |
| Tensile Strain at Yield, (23 °C, 50 mm/min) | 10 | % | ISO 527-1, -2 |
| Hardness | | | |
| Shore Hardness, (Shore D) | 70 | | ISO 868 |
| Thermal | | | |
| Vicat Softening Temperature, (A50) | 152 | °C | ISO 306 |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 88 | °C | ISO 75B-1, -2 |
| Optical | | | |
| Haze | 0.50 | % | ASTM D1003 |
| | | | |