



Moplen HP462S

Polypropylene, Homopolymer

Product Description

Moplen HP462S is a very narrow Molecular Weight Distribution homopolymer, suitable for extrusion applications. Moplen HP462S is designed for production of continuous filaments. Typical applications are HTY and spunbond nonwoven.

Product Characteristics

Test Method used	ISO
Processing Methods	Continuous Filament/Spinning
Features	Controlled Rheology, Gas-fading Resistant, Homopolymer, Narrow Molecular Weight Distribution
Typical Customer Applications	Filament Yarn, Furniture & Buildings, Geotextile & Agriculture, Hygiene Nonwoven, Nonwoven Spunbond, Protective Clothes

Typical Properties	Method	Value	Unit
Physical			
Melt flow rate (MFR)	ISO 1133	36	g/10 min
Mechanical			
Tensile Modulus	ISO 527-1, -2	1450	MPa
Tensile Stress at Yield	ISO 527-1, -2	34	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	8	%
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	85	°C
Vicat softening temperature	ISO 306		
(B50 (50°C/h 50N))		90	°C
(A50 (50°C/h 10N))		154	°C