

## **Technical Data Sheet**

## Pristene RM5500

Polypropylene, Random Copolymer



## **Product Description**

*Pristene* RM5500 is a metallocene polypropylene random copolymer with ultra high clarity and gloss, high purity, good stiffness and impact balance and low volatile content. Typical customer applications are baby feed bottles (IBM/ISBM), transparent containers, food containers, cosmetic containers.

**Application** Clear Containers; Housewares

Market Consumer Products; Rigid Packaging

Processing Method Injection Blow Molding; Injection Molding; Injection Stretch Blow Molding

Attribute High Clarity; High Gloss; Random Copolymer

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ASTM D1238
Density	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	1400	MPa	ASTM D790
Tensile Strength at Yield	35	MPa	ASTM D638
Tensile Elongation at Yield	10	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	40	J/m	ASTM D256