



Sequel 1440HF-PUV

Compounded Polyolefin

Product Description

Sequel 1440HF-PUV engineered polyolefin material is designed for large automotive exterior applications that require ductile impact properties at low temperatures, excellent paintability, and processability.

Product Characteristics

Test Method used	ISO
Processing Methods	Injection Molding
Features	Ductile, Paintable, Good Processability
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.94	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	27	g/10 min

Mechanical

Flexural modulus	ISO 178	1200	MPa
------------------	---------	------	-----

Note: 80x10x4mm specimen

Additional Information

Mold shrinkage	ISO 294-4
----------------	-----------