

Technical Data Sheet

Softell™ TKG 300N C12616

Polypropylene Compounds

Product Description

Softell™ TKG 300N C12616 is a 25% glass fiber reinforced PP copolymer, with very low gloss, excellent emissions, excellent scratch resistance and very low CLTE (Coefficient of Linear Thermal Expansion). Please contact Basell for shrinkage recommendations. The product is available in different color matched, pellet form. This grade is delivered in C12616 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good UV Resistance; High Stiffness; Low Gloss; Pleasing Surface Appearance; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	1.09	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2500	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	34	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	35	kJ/m²	ISO 179-1/1eA
(-30 °C)	7.5	kJ/m²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	132	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	80	°C	ISO 75A-1, -2