

Technical Data Sheet

Softell TKS 209N NAT



Polypropylene Compounds

Product Description

Softell TKS 209N NAT is an unfilled PP copolymer, with very low rigidity, good scratch resistance and very low gloss. Product is also available as a customized color matched, pellet form. This grade is delivered in natural color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	6	g/10 min	ISO 1133-1
Density, (23 °C)	0.92	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	115	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched			
(23 °C)	No Break		ISO 179-1/1eA
(-30 °C)	100	kJ/m ²	ISO 179-1/1eA