

## **Technical Data Sheet**

## Schulink XL 351-2363G GREY UNBLENDED



Polyethylene, Crosslinked

## **Product Description**

*Schulink* XL 351-2363G GREY UNBLENDED is a Polyethylene, Crosslinked material and is typically used in Rotational Molding applications. Features include: UV Stabilized.

Processing Method Rotomolding
Attribute UV Stabilized

Forms Powder

Appearance Colors Available

Application Agricultural; Automotive Under the Hood; High Temperature Applications; Lawn &

Garden Equipment; Tanks

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Density - Specific Gravity	0.942	g/cm³	ASTM D792
Mechanical			
Tensile Strength at Yield, (51 mm/min, Rotational Molded)	19.0	MPa	ASTM D638
Environmental Stress Crack Resistance			
(Compression Molded, F50, 100% Igepal)	1000	hr	ASTM D1693
(Compression Molded, F50, 10% Igepal)	1000	hr	ASTM D1693
Flexural Modulus, (Rotational Molded, 1% Secant)	689	MPa	ASTM D790
Tensile Elongation at Break, (51 mm/min, Rotational Molded)	500	%	ASTM D638
Impact			
Impact Strength			
(-40 °C, 3.18 mm, Rotational Molded)	81	J	ARM
(-40 °C, 6.35 mm, Rotational Molded)	>251	J	ARM
Thermal			
Deflection Temperature Under Load Unannealed (264 psi), (Rotational Molded)	35.1	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi), (Rotational Molded)	62.0	°C	ASTM D648