

## **Technical Data Sheet**

## Polyaxis LP 8000-7764 HABANERO PELL



Polyethylene, High Density, Metallocene

## **Product Description**

*Polyaxis* LP-8000 is a high density polyethylene intended for the rotational molding industry. This stiff yet tough compound has been used in watercraft with good success.

Processing MethodRotomoldingFormsPellets; PowderAppearanceColors Available

Additive Long Term UV-10 Stabilizer

|  | Nominal |          |             |
|--|---------|----------|-------------|
| Typical Properties   | Value   | Units    | Test Method |
| Physical   |         |          |             |
| Melt Flow Rate, (190 °C/2.16 kg)   | 3.6     | g/10 min | ASTM D1238  |
| Density - Specific Gravity   | 0.945   | g/cm³    | ASTM D792   |
| Mechanical   |         |          |             |
| Tensile Strength at Yield, (51 mm/min, Rotational Molded)                            | 22.1    | MPa      | ASTM D638   |
| Environmental Stress Crack Resistance, (Compression Molded, F50, 10% Igepal)         | 6.00    | hr       | ASTM D1693  |
| Flexural Modulus, (Rotational Molded, 1% Secant)                                     | 1000    | MPa      | ASTM D790   |
| Tensile Elongation at Break, (51 mm/min, Rotational Molded)                          | 500     | %        | ASTM D638   |
| Impact   |         |          |             |
| Impact Strength  |         |          |             |
| (-40 °C, 3.18 mm, Rotational Molded)   | 88      | J        | ARM         |
| (-40 °C, 6.35 mm, Rotational Molded)   | >258    | J        | ARM         |
| Thermal  |         |          |             |
| Deflection Temperature Under Load Unannealed (264 psi), (3.18 mm, Rotational Molded) | 39.3    | °C       | ASTM D648   |
| Deflection Temperature Under Load Unannealed (66 psi), (3.18 mm, Rotational Molded)  | 71.1    | °C       | ASTM D648   |