

CELSTRAN® ABS-GF40-05 NATURAL

CELSTRAN® Long Fibre

Celstran Long Fiber Reinforced ABS-GF40-05 Natural is a 40% long glass ABS, This material imparts excellent impact and modulus properties that exceed that of short fiber ABS.

Product information

Resin Identification	ABS-LGF40	ISO 1043
Part Marking Code	>ABS-LGF40<	ISO 11469

Typical mechanical properties

Tensile modulus	10600 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	98 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.1 %	ISO 527-1/-2
Flexural modulus	10900 MPa	ISO 178
Flexural strength	180 MPa	ISO 178
Charpy notched impact strength, 23°C	28 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34 ^[C]	

[C]: Calculated

Injection

Back pressure	3 MPa
---------------	-------

Characteristics

Processing	Injection Moulding
Delivery form	Pellets

Additional information

Processing Notes

Pre-Drying

CELSTAN PC/ABS should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.