



ATEVA® 2803A

ATEVA®

Product information

Resin Identification (EVAC) ISO 1043
Part Marking Code >(EVAC)< ISO 11469
Vinyl acetate content 28 %

Rheological properties

Melt Flow Index

Temperature

190 °C

Load

ASTM D 1238

190 °C

2.16 kg

Typical mechanical properties

Tensile Strength	24	MPa	ASTM D 638
Elongation at break	770	%	ASTM D 638
Flexural modulus	21	MPa	ASTM D 790
Brittleness Temperature	<-85	°C	ASTM D 746
Shore A hardness	81		ASTM D 2240
Shore D hardness	28		ASTM D 2240

Thermal properties

Melting temperature 75 °C ASTM D 3418 Ring and ball softening point 172 °C ASTM E 28

Physical/Other properties

Density 952 kg/m³

Printed: 2025-05-28 Page: 1 of 1

Revised: 2025-03-07 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any e

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.