

GUR® 4018 EP ECO-B

GUR®

Melt processable HMW-PE powder grade

GUR® 4018 EP ECO-B incorporates >99% of bio-circular ethylene by weight in the finished product through mass balance allocation. The product is a drop-in replacement to the standard grade with the same performance and processing properties and contributes to the displacement of virgin fossil fuel resources. The biobased source and allocated content in the product are certified according to ISCC PLUS mass balance approach.

Samples of the above listed GUR® product are tested according to the requirements described in monograph 3.1.3. of Ph.Eur. 10.0 "Polyolefines". The results of those tests indicated the sampled material was compliant with monograph 3.1.3 of Ph.Eur. 10.0.

Please note that the manufacturer or seller of parts and articles made out of the above mentioned products have to take the full responsibility regarding applicable legal requirements.

Product information

Resin Identification	(PE-HMW)	ISO 1043
Part Marking Code	>(PE-HMW)<	ISO 11469
Average molecular weight	600000 g/mol	Margolies' equation
Average particle size, d50	115 µm	laser scattering

Rheological properties

Melt mass-flow rate	1.1 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	500 cm³/g	ISO 307, 1628

Typical mechanical properties

Tensile modulus	1050 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	25 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	8 %	ISO 527-1/-2
Tensile stress at 50% strain	18 MPa	ISO 527-1/-2
Tensile stress at break, 50mm/min	37 MPa	ISO 527-1/-2
Nominal strain at break	870 %	ISO 527-1/-2
Elongational stress F, 150/10	0.01 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	45 kJ/m²	ISO 21304-2
Poisson's ratio	0.45 ^[C]	

[C]: Calculated

Tribological properties

Wear by sandslurry method (based on GUR 4120=100)	250
--	-----

Thermal properties

Temperature of deflection under load, 1.8 MPa	43 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	80 °C	ISO 306

GUR® 4018 EP ECO-B

GUR®

Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
--------------------	------------	---------------

Physical/Other properties

Density	950 kg/m ³	ISO 1183
Bulk density	450 kg/m ³	ISO 60

Characteristics

Processing	Injection Moulding, Porous Sintering
Delivery form	Powder
Special characteristics	High impact or impact modified, Hydrolysis resistant, Low wear / Low friction, Chemical resistant
Sustainability	Bio-Content