

VECTRA® S471

Liquid Crystal Polymer

High flow, High Heat resistance, Low Warpage, for Thick Walled (>0.2mm) or thin (< 0.2mm) & Thick Walled combination parts.

Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant

UL-Listing V-0 in natural and black at 0.4mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electricals 130°C, mechanicals 130°C. UL = Underwriters Laboratories (USA)

Product information

Resin Identification	LCP-(GF+MD)4 6	ISO 1043
Part Marking Code	>LCP-(GF+MD)46<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.2 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.5 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	13000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	110 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.1 %	ISO 527-1/-2
Flexural modulus	14000 MPa	ISO 178
Flexural strength	170 MPa	ISO 178
Flexural strain at failure	2 %	ISO 178
Charpy impact strength, 23°C	10 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	7 kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	5.0 kJ/m ²	ISO 180/1A
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10°C/min	350 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	315 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	271 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	8 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	17 E-6/K	ISO 11359-1/-2
Specific heat capacity solid	1260 J/(kg K)	ISO 22007-4

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
-------------------------------	-----------	-----------------

VECTRA® S471

Liquid Crystal Polymer

Electrical properties

Relative permittivity, 1MHz	4	IEC 62631-2-1
Dissipation factor, 1MHz	70 E-4	IEC 62631-2-1
Volume resistivity	1E14 Ohm.m	IEC 62631-3-1
Surface resistivity	1E11 Ohm	IEC 62631-3-2
Comparative tracking index	200	IEC 60112
Comparative tracking index, 100 drops	200	IEC 60112

Physical/Other properties

Density	1760 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	150 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.01 %
Melt Temperature Optimum	365 °C
Min. melt temperature	360 °C
Max. melt temperature	375 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Back pressure	3 MPa
Ejection temperature	290 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Flame retardant, Heat stabilised or stable to heat, High Flow, Low Warpage, Lead-free soldering resistant

Additional information

Injection molding

Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra S-grades should be dried at 150 °C for a minimum of 6 hours or at 170 °C for a minimum of 4 hours in a desiccant dryer.

Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: ½ feed, ¼ compression, ¼ metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the mold temperature can be increased.

VECTRA® S471

Liquid Crystal Polymer

injection velocity to improve melt flow.

Processing Notes

Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -40^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V ($\leq 24\text{ h}$).